



Innovation and Experience at Work

RheoGel 784

RheoGel 784 is an electrically conductive synthetic hydrocarbon grease fortified with an effective rust inhibitor.

BASE OIL CHARACTERISTICS		TYPICAL VALUE *
Type		Synthetic Hydrocarbon
Temperature Service Range (°C)		-40 to 125
GREASE CHARACTERISTICS		TYPICAL VALUE *
Thickener		Conductive Carbon
Color		Black
Appearance		Smooth
NLGI Grade		2
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	265-295
	Worked	60X 265-295
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)		260 min.
Oil Separation (ASTM D6184)	24h at 100°C	0.1%
Evaporation (CTM-1)	24 at 100°C	0.0%
Volume Resistivity, RT (CTM)		62 ohm-cm

Engineered Custom Lubricants

ISO/TS16949:2009 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: customerservice@ecllube.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications. ECLI Products, LLC, owns and does business as Engineered Custom Lubricants and Lubrication Technology.