



Innovation and Experience at Work

UltraSil 475

A wide temperature, transparent silicone grease that is intended for applications that could have exposed grease, but grease visibility is not desired. Its clear consistency makes it difficult to detect visually on most surfaces. This grease also possesses outstanding cold temperature capabilities, has very low evaporation and is compatible with most plastics and elastomers.

BASE OIL CHARACTERISTICS		TYPICAL VALUE *
Type		Silicone
Temperature Service Range (°C)		-50 to 200
GREASE CHARACTERISTICS		TYPICAL VALUE *
Thickener		Silica
Color		Clear
Appearance		Smooth
NLGI Grade		1.5
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	298
	Worked	302
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)		260 min.
Oil Separation (ASTM D6184)	24h at 100°C	0.10%
Evaporation (CTM-1)	24h at 100°C	0.06%
Water Washout (ASTM D1264 / DIN 51807-T2)	60 min at 41°C	0.70%
Water Washout (ASTM D1264 / DIN 51807-T2)	60 min at 79°C	1.31%
Specific Gravity (CTM-2)	25°C	0.98
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	15 min, 1200 RPM, 25psi, 75°C, 40kg	1.27mm
	Dynamic Coefficient of Friction (steel on steel)	0.300
Apparent Viscosity (Brookfield Viscometer T-C spindle 1 rpm)	-40°C	1,500,000 cP

Engineered Custom Lubricants

ISO/TS16949:2009 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: customerservice@eclube.com • www.eclube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications. ECLI Products, LLC, owns and does business as Engineered Custom Lubricants and Lubrication Technology.